NO.	PARAMETERS	PLA+	ABS+
1	NOZZLE TEMPERATURE	<b>190-220°c</b> (Recomanded) -It depands on	<b>225-250°c</b> (Recomanded) -It depands on
		Printer model, Print speed and Nozzle size	Printer model, Print speed and Nozzle size
2	BED TEMPERATURE	<b>50-60°c</b> ( Recommended) , Print can be done without heating bed.	<b>100-120°c</b> ( Recomanded)
3	SPEED	50-70 mm/sec	50-70mm/sec
4	PART COOLING FAN	100% from second layer ( Recomanded)	Not recommended , Only use for small models if required
5	HOTEND TYPE	PETF lined hotend ( Recomanded)	Any type
6	ENCLOSURE	Not required	Recomanded
7	RETRACTION	Required ( Caliberation based on printer model)	Required ( Caliberation based on printer model)